

★ CAT 03.01 · POLYASPARTIC · PA-200 · TDS REV 01 · 04/2026

90% Solids Polyaspartic.

★ UV-STABLE · SELF-LEVELING · HIGH-GLOSS CLEAR TOPCOAT

Self-leveling, 90% solids polyaspartic floor coating with superior wetting, long work time, excellent adhesion, and broad chemical resistance. Non-yellowing under UV. Engineered to lock in flake or metallic systems and finish at high gloss.

§ 01 · CURE & WORK TIME

TEMPERATURE	41°F	68°F	75°F
POT LIFE	45 min	35 min	30 min
SET-TO-TOUCH	4 hr	2-4 hr	1-2 hr
DRYING TIME	12-16 hr	6-12 hr	6-8 hr
DRY-THROUGH	36 hr	24 hr	16-24 hr
MATURATION	7 days	7 days	7 days

Times measured under controlled lab conditions and may vary on site. Coating that exceeds the recoat window may exhibit adhesion failure — verify surface prep before recoating.

§ 02 · MATERIAL DATA

SOLIDS BY VOLUME	90%
MIX RATIO (A : B, WT.)	1 : 1
THEORETICAL COVERAGE	250 SF/GAL @ 8 mil DFT
RECOMMENDED DFT	8 – 12 mil
COLOR	Clear (compounds)
GLOSS @ 60°	> 90 (high gloss)
SPECIFIC GRAVITY	≈ 1.0
THINNER / DILUTION	Not applicable
SHELF LIFE (SEALED)	12 months
PACKAGING	Pails (compounds)

§ 03 · APPLICATION

01 · SUBSTRATE

Concrete cured ≥ 28 days at ≥ 70°F with relative humidity ≤ 50%. Surface free of oil, dust, sand, laitance. Substrate moisture ≤ 6%.

03 · MIX

1 : 1 by weight, Part A into Part B. Power mix 3 minutes at 400–600 RPM. Use within 30 minutes at 75°F (longer in cooler conditions).

02 · CONDITIONS

Atmosphere 41–95°F. Surface ≤ 104°F. RH ≤ 80%. Reinforce cracks and wall/floor joints with epoxy filler before the first coat.

04 · APPLY

Apply with industrial-grade trowel squeegee at 8–12 mil DFT. Thinner-than-spec coverage may cause cratering, skid marks, or whitening streaks.

★ PA-200 · TECH DATA · CONTINUED

Physical Properties.

★ ASTM-METHOD VERIFIED

PROPERTY	TEST METHOD	RESULT
Adhesion / bond strength	ASTM D4541	> 500 PSI · 100% concrete failure
Compressive strength	ASTM D695	22,600 PSI
Flexural strength	ASTM D790	18,500 PSI
Tensile strength	ASTM D638	10,500 PSI
Elongation	ASTM D638	10%
Hardness, Shore D (24 hr)	ASTM D2240	80 – 82
Taber abrasion (CS-17, 1000 g)	ASTM D4060	40 mg loss / 1000 cycles
Abrasion resistance	ASTM D4060	0.15 g (CS-17 / 1000 cycles)
Impact resistance	ASTM D2794	2.5 ft·lb
Wet DCOF (slip resistance)	ASTM A326.3	> 0.62
Gloss @ 60°	ASTM D523	> 90
Flammability	—	Not applicable

§ 04 · STORAGE & HANDLING

Store sealed pails between 50–80°F, away from direct sunlight and ignition sources. Twelve-month shelf life from the manufacture date stamped on the pail. Once opened, mixed material is single-use and cannot be returned to container. Refer to the corresponding Safety Data Sheets (SDS Part A and Part B) for full handling, PPE, and disposal guidance.

§ 05 · DISCLAIMER

The information in this technical data sheet is provided in good faith and to the best of Resin Source LLC's knowledge at time of publication. Resin Source LLC makes no warranty, express or implied, as to the accuracy, completeness, or fitness of this data for any specific application. Field conditions vary; users are responsible for verifying suitability with a job-site test patch and consulting current Safety Data Sheets before use. Resin Source LLC reserves the right to revise specifications without prior notice and shall not be liable for incidental or consequential damages arising from reliance on this document. © 2026 Resin Source LLC. All rights reserved.